

Life and Performance of GS Yuasa's Generation 4 Lithium-ion Chemistry for Space Applications

2023 Space Power Workshop

April 25-27, 2023



Curtis Aldrich, George Bergmark, Tom Pusateri - GYLP Go Honda, Yui Sakamoto, Masazumi Segawa - GYT

GS Yuasa Company Overview



lithium-ion batteries for submarines



YUASA (Yuasa Corporation)

Receiving orders of lithium-ion battery system for Boeing 787 in the U.S.

GS Yuasa Aerospace and Specialty Battery Groups



GS Yuasa Technology Ltd. "GYT"

- Research, development, manufacturing, test, and sales of specialty cells and batteries for:
 - o Aerospace
 - o Undersea
 - Defense and Security
- ISO9001 & JISQ9100 certified
- Headquarters located in Kyoto, Japan

GS Yuasa Lithium Power, Inc. "GYLP"

- Primary channel for GS Yuasa Li-ion energy storage technologies and solutions for North American aerospace and defense applications.
- Engineering, sales, service, manufacturing, program management, logistics and export compliance
- ISO9001 & AS9100 certified
- Incorporated in the state of Georgia, US Company



RECIPROCAL DEFENSE PROCUREMENT MOU June 2016, extended through June 2031

 $\ensuremath{\mathbb{C}}$ 2023 by GS Yuasa Lithium Power Inc. Published by The Aerospace Corporation with permission



GS Yuasa LSE Li-ion Cell for Space Overview

GS Yuasa Space Flight Heritage Update



GS Yuasa is a world leader in Li-ion energy storage for space vehicles

Number of satellites	234+	
– LEO/MEO	108+	
- GEO	124	4
 Interplanetary 	2+	1
1 st satellite on-orbit	Servis 1 (30 Oct. 2003)	
Longest satellite on-orbit (yrs)	>18yr (IPSTAR, 11 Aug. 2005) still operational
Li-ion Watt-hours flown in space	>4.69 MWh (world leader)	
Cell-hours flown in space	>573 million hours	
Space cell qualification programs	>27	
Cell sizes (Ah) flown	35; 50; 55; 100; 102; 110;	
	134; 145; 175; 190; 200	and see

Performance to date	No failures
Backlog (Wh)	>1.20 MWh

Launch vehicles & number of satellites

Ariane-5ECA	51	Soyuz-STB Fregat-MT	17	Epsilon	6
Falcon 9	27	Antares 120, 230, 230+	15	Zenit-3	5
H-2A-20x	28	H-2B-304	13	Others	10
Proton-M Briz-M	29	Atlas 5 (401)	7		
Soyuz	27	Atlas 5 (421,431,551)	6		

Metrics updated February 2023
















GS Yuasa has demonstrated the ability to maintain configuration and control over the material sources for 15+years thanks to strong relationship with the suppliers of the materials.

Generation 4 LCO/Graphite Space Cell

- Generation 4 Cells (2019) Improvements to Generation 3 LCO/Graphite chemistry increase energy density while maintaining superb capacity retention and suppression of DCR growth.
 - \rightarrow Energy and Power optimized electrode optimizations will be available.

4	-	
-		

	160 Ah	145 Ah
	Generation 4	Generation 3
Dimensions	H 263*	H 263*
/ mm	W 130	W 130
	T 50	Т 50
EoCV / V	4.10	4.10
Capacity / Ah		
(Rated)	160	145
(Actual)	178	161
Discharge	3.72	3.70
Voltage / V		
Mass / kg	3.69	3.55
Specific energy	180	168
/ Wh/kg		*Excluding terminal stu



GSYUASA


ETS-9 (JAXA)

Minimum Design Changes Since 1999; Enhancements Only

LSE Cell Basic Shape

Over 25 years of outstanding performance







The LSE cell portfolio consists of various sizes of Li-ion cells. All cells share the same primary features: Al-case, wound-prismatic construction, ceramic terminals, LCO chemistry. All are manufactured in Kyoto, Japan on the same equipment and using the same basic processes. The portfolio can be viewed as a single fundamental cell technology, configurable in height, width and thickness.


LSE12x Cell Case

Fusion of Aviation and Automotive Cells



Blue Energy

- EH5 Ultra high power cell for Honda/Acura hybrids



- Inspired by mature commercial cell designs; Enhanced for space
 - Case neutral design
 - Radiation hardened
 - Hermetically sealed
- Power optimized Gen 4 chemistry suitable for all space vehicles

100Ah Class Cell, Energy Type




	Cell	Nominal BOL	EoCV	BOL
	Cell	Ah Capacity	EUCV	BOL Wh/Kg
Gen1	LSE100	107	3.98	141

GSYUASA

Width	Thick	Height*
130	50	208



100Ah Class Cell, Energy Type




	Cell	Nominal BOL	Fact	BOL
		Ah Capacity	EoCV	BOL Wh/Kg
Gen1	LSE100	107	3.98	141
Gen2	LSE100	109	3.98	144

GSYUASA

Width	Thick	Height*
130	50	208



100Ah Class Cell, Energy Type



	Cell	Nominal BOL Ah Capacity	EoCV	BOL Wh/Kg
Gen1	LSE100	107	3.98	141
Gen2	LSE100	109	3.98	144
Gen3	LSE110	122	4.1	165


GSYUASA

Width	Thick	Height*
130	50	208





100Ah Class Cell, Energy Type




	Cell	Nominal BOL	EoCV	BOL
	Cell	Ah Capacity	EUCV	Wh/Kg
Gen1	LSE100	107	3.98	141
Gen2	LSE100	109	3.98	144
Gen3	LSE110	122	4.1	165
Gen4	LSE122	132	4.1	175

Width	Thick	Height*		
130	50	208		



100Ah Class Cell, Energy Type



Cell		Nominal BOL	Facy	BOL
		Ah Capacity	EoCV	Wh/Kg
Gen1	LSE100	107	3.98	141
Gen2	LSE100	109	3.98	144
Gen3	LSE110	122	4.1	165
Gen4	LSE122	132	4.1	175

GSYUASA

Width	Thick	Height*		
130	50	208		






Generation 4 Qualification Status and Life Performance

Gen IV LSE Cell Configurations & Qualification Status





The available LSE cell form factors will remain constant with 5 cell sizes available. GS Yuasa has manufactured >17,000 "LSE" cells for space applications totaling more than >6.85MWh of energy storage for this design.


Naming convention is the prefix "LSE" followed by the nameplate capacity. All C-rates are in reference to this nameplate capacity.

use rives feetracky Ltd.			Chem	nistry	Dimensions			
	Gen 3		n 3	Ge	n 4	Width	Thick	Uoight*
		Energy	Power	Energy	Power	wiath	Thick	Height*
L					LSE12x	133	21	68.2
		LSE42	LSE38	TBD	TBD	98	37	151
Cell		LSE55	LSE51	LSE60	LSE56	130	50	123
Configurati	on	LSE110	LSE102	LSE120	LSE112	130	50	208
		LSE145	LSE134	LSE160	LSE147	130	50	263
		LSE190		LSE205	TBD	165	50	263

*not including terminal posts

Gen IV LSE Cell Configurations & Qualification Status





*not including terminal posts

Generation 4 Life Testing



				Test Cor	ditions	;		A		
Test Name.	Cell Type	Charge Condition (CCCV unless noted)			Discharge Condition			Ambient Test Temp	Number of Cycles	Remark
		EoCV	Rate	Time	EoDV	Rate	Time	Temp		
Energy Cell Testing										
100% DoD Cycling	LSE160	4.10V	80A	4.0hr	2.75V	100A	N/A	25°C	4,500	
80% DOD GEO	LSE160	4.10V	32A	10.8hr	N/A	107A	1.2hr	15°C	2,500	Cont. Deep DoD GEO Cycle
60% DoD GEO	LSE160	4.10V	32A	10.8hr	N/A	80A	1.2hr	15°C	2,100	Nominal DoD GEO Cycle
40% DoD LEO	LSE160	4.10V	80A	1.0hr	N/A	120A	0.53Hr	15°C	16,000	Deep DOD LEO Cycle
25% DoD LEO	LSE160	4.10V	48A	1.0hr	N/A	80A	0.5Hr	15°C	16,000	Nominal DOD LEO Cycle
				Power (Cell Tes	ting				
100% DoD Cycling	LSE112	4.10V	56A	4.0hr	2.75V	100A	N/A	25°C	4,500	
40% DoD LEO	LSE112	4.10V	56A	1.0hr	N/A	89.6A	0.5hr	20°C	19,500	Deep LEO Cycle
25% DoD LEO	LSE112	4.10V	56A	1.0hr	N/A	89.6A	0.5hr	20°C	19,500	Deep LEO Cycle
40%,50% ,60% and 70% DoD LEO	LSE12x	4.10V	Various	1.0Hr	N/A	Various	0.5hr	15°C	15000+	Ultra Deep DOD LEO Cycling

Above table is not a comprehensive list of all life cycle testing available. Please contact GYLP to request.

Generation 4 Life Testing



				Test Con	ditions	;				
Test Name.	Cell Type	Charge Condition (CCCV unless noted)			Disc	harge Coi	ndition	Ambient Test Temp	Number of Cycles	Remark
		EoCV	Rate	Time	EoDV	Rate	Time	iemp		
Energy Cell Testing										
100% DoD Cycling	LSE160	4.10V	80A	4.0hr	2.75V	100A	N/A	25°C	4,500	
80% DOD GEO	LSE160	4.10V	32A	10.8hr	N/A	107A	1.2hr	15°C	2,500	Cont. Deep DoD GEO Cycle
60% DoD GEO	LSE160	4.10V	32A	10.8hr	N/A	80A	1.2hr	15°C	2,100	Nominal DoD GEO Cycle
40% DoD LEO	LSE160	4.10V	80A	1.0hr	N/A	120A	0.53Hr	15°C	16,000	Deep DOD LEO Cycle
25% DoD LEO	LSE160	4.10V	48A	1.0hr	N/A	80A	0.5Hr	15°C	16,000	Nominal DOD LEO Cycle
				Power C	Cell Tes	ting				
100% DoD Cycling	LSE112	4.10V	56A	4.0hr	2.75V	100A	N/A	25°C	4,500	
40% DoD LEO	LSE112	4.10V	56A	1.0hr	N/A	89.6A	0.5hr	20°C	19,500	Deep LEO Cycle
25% DoD LEO	LSE112	4.10V	56A	1.0hr	N/A	89.6A	0.5hr	20°C	19,500	Deep LEO Cycle
40%,50% ,60% and 70% DoD LEO	LSE12x	4.10V	Various	1.0Hr	N/A	Various	0.5hr	15°C	15000+	Ultra Deep DOD LEO Cycling

Above table is not a comprehensive list of all life cycle testing available. Please contact GYLP to request.


LSE160 – 100% DOD Cycle Life

Generation 4 Energy Type



	Test Conditions								
		ndition		ischar	Ambient Test				
(CCCV unless noted)				onditio	Temp				
EoCV	Rate	Time	EoDV	Rate	Time	icinp			
4.10V	80A (0.5C)	4hr	2.75V	100A	N/A	25°C			

Generation 4 provides ~10% Ah increase from Generation 3 with similar retention characteristics



LSE160 - 100% DOD Cycle Capacity Retention


LSE160 – 100% DOD Cycle Life

Generation 4 Energy Type



	Test Conditions								
Cha	Ambient								
(CCCV unless noted)			Co	onditio	Test				
EoCV	Rate	Time	EoDV	Rate	Time	Тетр			
4.10V	80A (0.5C)	4hr	2.75V	100A	N/A	25°C			

Generation 4 provides ~10% Ah increase from Generation 3 with similar retention characteristics



LSE160 - 100% DOD Cycle Capacity Retention

LSE160 – 80% DOD Cycle Life (GEO)


Generation 4 Energy Type



	Ambient							
Charge Condition Discharge								
(CCCV unless noted)			Co	onditio	Test			
EoCV	Rate	Time	EoDV	Rate	Time	Тетр		
4.10V	32A (0.2C)	10.8hr	N/A	107A (0.67C)	1.2hr	15°C		

Accelerated 80% DOD GEO cycling profile. 2 cycles per day with no solstice periods.

Cycle count already exceeds typical 15 year GEO profile



LSE160 – 80% DOD Cycle Life (GEO)

Generation 4 Energy Type




	Test Conditions							
Charge Condition Discharge						Ambient Test		
(CCCV unless noted)			С	onditio				
EoCV	Rate	Time	EoDV	Rate	Time	Тетр		
4.10V	32A (0.2C)	10.8hr	N/A	107A (0.67C)	1.2hr	15°C		

Accelerated 80% DOD GEO Cycle profile. 2 cycles per day with no

solstice periods.

Cycle count already exceeds typical 15 year GEO profile



LSE160 – 60% DOD Cycle Life (GEO)

Generation 4 Energy Type




	Test Conditions								
Cha	Ambient								
(CCCV unless noted)			Co	onditio	Test				
EoCV	Rate	Time	EoDV	Rate	Time	Тетр			
4.10V	32A (0.5C)	10.8hr	N/A	80A (0.5C)	1.2hr	15°C			

Accelerated 60% DOD GEO Cycle profile. 2 cycles per day with no

solstice periods.

Cycle count already exceeds typical 15 year GEO profile



LSE160 - 60% DOD Cycle Capacity Retention


LSE160 – 60% DOD Cycle Life (GEO)

Generation 4 Energy Type



	Test Conditions								
Cha	rge Coi	ge	Ambient Test						
(CCCV unless noted)			Co	onditio	Temp				
EoCV	Rate	Time	EoDV	Rate	Time	Temp			
4.10V	32A (0.5C)	10.8hr	N/A	80A (0.5C)	1.2hr	15°C			

Continuous cycling between 60% and 80% DOD show no adverse effects on Gen 4 performance.



LSE112 – 100% DOD Cycle Life

Generation 4 Power Type



	Ambiant					
Charge Condition (CCCV unless noted)			Discharge Condition			Ambient Test
EoCV	Rate	Time	EoDV	Rate	Time	Тетр
4.10V	56A (0.5C)	4.0hr	2.75V	100A	N/A	25°C

Generation 4 provides ~10% Ah increase from Generation 3 with similar retention characteristics

Capacity (Ah) -LSE112 E001 -LSE112 E002 -LSE102 (gen 3 ref.) **Cycle Count**

LSE112 - 100% DOD Cycle Capacity Retention


LSE112 – 100% DOD Cycle Life

Generation 4 Power Type



Test Conditions						Ambiant
Charge Condition (CCCV unless noted)			Discharge Condition			Ambient Test Temp
EoCV	Rate	Time	EoDV	Rate	Time	Temp
4.10V	56A (0.5C)	4.0hr	2.75V	100A	N/A	25°C

Gen 4 Power type Ah retention similar to Gen 3. Power type cells




LSE112 – 40% DOD Cycle Life (LEO)

Generation 4 Power Type



	Ambient					
Charge Condition (CCCV unless noted)			Discharge Condition		Test Temp	
EoCV	Rate	Time	EoDV	Rate	Time	Temp
4.10V	56A	1.0hr	N/A	89.6A	0.5hr	20°C

40% Deep DoD LEO cycling presents no issues for Gen 3 or Gen 4 chemistries.



LSE112 - 40% DOD LEO Cycle Results


LSE112 – 40% DOD Cycle Life (LEO)

Generation 4 Power Type



Test Conditions						Auchieut
Charge Condition			Discharge			Ambient Test Temp
(CCCV unless noted)		Condition				
EoCV	Rate	Time	EoDV	Rate	Time	iemp
4.10V	56A	1.0hr	N/A	89.6A	0.5hr	20°C

Gen. 4 Ah retention exhibits marginal improvement to Gen. 3



LSE112 - 40% DOD LEO Cycle Results

LSE12x – Ultra High DOD LEO Cycle Tests

New cell size, ultra high performance, Gen 4 Power Type




Charge Condition			Discharge			Ambient
(CCCV unless noted)		Condition			Test Temp	
EoCV	Rate	Time	EoDV	Rate	Time	
4.1V	Various	1.0Hr	N/A	Various	0.5hr	15°C

Cycle	Discharge	Charge
40%DOD	0.8C (9.6A) for 0.5hr	0.5C, 4.10V, CC/CV, 1hr
50%DOD	1.0C (12.0A) for 0.5hr	0.6C, 4.10V, CC/CV, 1hr
60%DOD	1.2C (14.4A) for 0.5hr	0.7C, 4.10V, CC/CV, 1hr
70%DOD	1.4C (16.8A) for 0.5hr	0.8C, 4.10V, CC/CV, 1hr

LSE12X Performance Specification


BOL Capacity	4.1V-2.75V	13.6 Ah, 51.0Wh		
	*4.2V-2.75V	15.0 Ah, 56.3Wh		
N	12 Ah, 45Wh			
Nominal	3.75 V			
Continuous	6A			
Continuo	24A			
Pul	60+A			
DCR (<6 mΩ			
Nomir	Nominal Cell Impedance			
	0.390 kg			



Summary




- GS Yuasa's Generation 4 LCO/Graphite chemistry provides meaningful performance increases from Generation 3 including:
 - Increased Energy Density
 - Excellent Capacity Retention under demanding cycle conditions
 - Decreased DCR for enhanced voltage performance under load
- Gen. 4 cells available from 12Ah to 205Ah in a single cell
 - LSE12x, LSE60, LSE112, LSE160, LSE205 Qualified
 - Energy and Power electrode optimizations



- LSE12x New 12Ah small form factor cell added to the portfolio
 - Enabling smaller spacecraft access to industry leading performance
 - Scalable battery designed and built by GYLP in Roswell, Ga.
 - Configurations ranging from 720Wh to 4,320Wh







Energy storage design test and manufacturing expertise Industry leading spaceflight heritage Validated and reliable performance modelling

